



EP 1 094 104 A1

EUROPEAN PATENT APPLICATION

(51) Int. Cl.⁷: **C10M 169/04**, G11B 19/20
// (C10M169/04, 105:36,
105:38, 133:06, 133:08, 135:10,
137:02), C10N30:14,
C10N40:18

(22) Date of filing: 20.10.2000

- **Yoshizaki, Koji,**
c/o Koyo Seiko Co., Ltd
Osaka 542-0081 (JP)
- **Komiya, Hiroshi,**
c/o Koyo Seiko Co., Ltd
Osaka 542-0081 (JP)


(74) Representative:
Selting, Günther, Dipl.-Ing. et al
Patentanwälte
von Kreisler, Selting, Werner
Postfach 10 22 41
50462 Köln (DE)

(72) Inventors:
• Suekuni, Noriko (née Kato),
c/o Koyo Seiko Co.,Ltd
Osaka 542-0081 (JP)

(57) There is provided is a conductive lubricant for a fluid dynamic bearing being able to ground static electricity occurring at the fluid dynamic bearing without impairing the performance of the fluid dynamic bearing. This conductive lubricant for a fluid dynamic bearing is provided by an ester base oil such as dioctyl sebacate that concurrently has heat resistance, a small quantity of evaporation, low cost and wettability to metal, which are necessary for a fluid dynamic bearing. The conduc-

tive lubricant contains 0.1 to 5 percent by weight of anti-static additive such as alkyl aryl sulfonate having an affinity for this ester base oil. Therefore, this antistatic additive imparts conductivity to the base oil, by which the static electricity occurring at the fluid dynamic bearing can be grounded without impairing the lubrication performance.

Fig. 1



Description

BACKGROUND OF THE INVENTION

[0001] The present invention relates to a conductive lubricant for a fluid dynamic bearing to be assembled into, for example, an HDD (hard disk drive).

[0002] Fluid dynamic bearings are increasingly employed in HDD's in order to provide an increased capacity.

[0003] There has conventionally been a fluid dynamic bearing, in which a lubricating oil of an ester-based oil such as diester and polyolester or a polyalkylene glycol oil is interposed between a body of rotation and a bearing member for supporting this body of rotation. This ester-based oil can generate a stable dynamic pressure even when the temperature changes, because it has excellent fluidity at low temperature and a small change in viscosity with respect to temperature change as well as excellent heat resistance.

[0004] As an ester-based oil, the conventionally known diester, polyolester or the like is employed. Examples of diester include adipic acid di(2-ethylhexyl) ester (DOA), diisodicyl adipate (DIDA), diisononyl adipate (DINA), di(2-ethylhexyl) azelate (DOZ) and di(2-ethylhexyl) sebacate (DOS). Examples of polyolester include hindered alcohol esters of neopentylglycol (NPG), trimethylolpropane (TMP) and pentaerythritol (PE). These base oils are employed singly or in mixture taking the torque characteristic and operating life of lubrication into consideration.

[0005] However, these oils exhibit a very high volume resistivity as apparent from the volume resistivity of each oil indicated in Table 1 below.

Table 1

Oil Type	Volume Resistivity (Ωcm) (20°C)
Mineral Oil	10^{14} or greater
Diester Oil	10^{11} - 10^{12}
Polyolester Oil	7×10^{12}
Polyalkylene Glycol Oil	1.2×10^9

[0006] If an MR head (magneto-resistive head), which is the other contributor to the increase in capacity, is combined with the fluid dynamic bearing, then the head side (stationary side) and the disk side (rotary side) are completely put in a contactless state in operation. Therefore, in this case, it is required to ground the static electricity occurring at the fluid dynamic bearing, for the protection of the MR head that is vulnerable to static electricity.

SUMMARY OF THE INVENTION

[0007] Accordingly, the object of the present invention is to provide a conductive lubricant for a fluid dynamic bearing, the conductive lubricant being able to ground the static electricity occurring at the fluid dynamic bearing.

[0008] In order to achieve the aforementioned object, the present invention provides a conductive lubricant for a fluid dynamic bearing comprising:

an ester base oil and an antistatic additive having an affinity for the ester base oil, and the antistatic additive being contained at 0.1 to 5 percent by weight in the conductive lubricant.

[0009] According to the present invention, an ester base oil that concurrently has heat resistance, a small quantity of evaporation, low cost and wettability to metal, which are necessary for a fluid dynamic bearing is employed, and an antistatic additive having an affinity for this ester base oil is contained at 0.1 to 5 percent by weight in the conductive lubricant. Therefore, according to the present invention, the conductive lubricant having conductivity by virtue of the antistatic additive contained in the conductive lubricant makes the rotary side and the fixed side of the fluid dynamic bearing electrically conductive. Therefore, the static electricity occurring on the rotary side of the fluid dynamic bearing can be earthed on the fixed side. The antistatic additive has an affinity for the ester base oil, and therefore, the lubrication performance is not impaired.

[0010] It is to be noted that the conductivity of oil becomes insufficient if the antistatic additive content is smaller than 0.1 percent by weight and becomes incapable of sufficiently discharging the static electricity. If the antistatic additive content exceeds 5 percent by weight, then the lubrication performance of oil is impaired.

[0011] In one embodiment, the antistatic additive is contained at 0.5 to 2 percent by weight in the conductive lubricant.

[0012] In the above embodiment, the antistatic additive is contained at 0.5 to 2 percent by weight, and therefore, the conduction performance and lubrication performance of oil can be made compatible at the more desired level.

[0013] In one embodiment, an anionic, cationic, amphoteric or nonionic antistatic additive is used as the antistatic additive.

BRIEF DESCRIPTION OF THE DRAWING

[0014] The present invention will become more fully understood from the detailed description given hereinbelow and the accompanying drawings which are given by way of illustration only, and thus are not limitative of the present invention, and wherein:

Fig. 1 is a schematic sectional view showing a fluid dynamic bearing for an HDD provided with a conductive lubricant for a fluid dynamic bearing according to an embodiment of the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0015] The present invention will be described in detail below on the basis of the embodiment shown in the drawing.

[0016] Fig. 1 shows a fluid dynamic bearing 1 and an MR head 2 constituting an HDD. This fluid dynamic bearing 1 is provided with a shaft 3 and a housing 5 for housing this shaft 3, and fluid dynamic pressure generating grooves 6 are formed on the outer peripheral surface of the shaft 3. Then, a conductive oil (not shown) according to the embodiment of the present invention is interposed between this shaft 3 and a bearing portion 15 of the housing 5.

[0017] This conductive oil includes 97.5 percent by weight of dioctyl sebacate (DOS) that serves as an ester base oil, 1.0 percent by weight of alkyl aryl sulfonate that serves as an anionic antistatic additive and 0.5 percent by weight of amine-based antioxidant. The ester base oil is an oil that concurrently has heat resistance, a small quantity of evaporation, low cost and wettability to metal, which are necessary for a fluid dynamic bearing. Further, the dioctyl sebacate employed as the ester base oil has a kinematic viscosity of 5 to 30 cSt (centistokes) and a viscosity index of not smaller than 110 at a temperature of 40°C. At this viscosity level, dioctyl sebacate causes no increase in consumption of power of a drive motor 11 and is suitable as a lubricant for the HDD fluid dynamic bearing.

[0018] It is to be noted that alkyl aryl sulfonate that serves as the anionic antistatic additive is a salt of neutralization of alkyl benzene sulfonate and alkylamine.

[0019] If the drive motor 11 constructed of a coil and a magnet is driven concerning the fluid dynamic bearing 1 constituting the HDD shown in Fig. 1, then the shaft 3 rotates relative to the housing 5, and the fluid dynamic pressure generating grooves 6 generate a fluid dynamic pressure in the conductive oil filled between the housing 5 and the bearing, portion 15 of the shaft 3, thereby supporting the shaft 3 in the radial direction relative to the housing 5. In this state, the MR head 2 located on the fixed side reads information from a magnetic disk 12 that is rotating together with the shaft 3.

[0020] According to this embodiment, the ester base oil (dioctyl sebacate) having conductivity by virtue of the anionic antistatic additive makes the shaft 3 of the fluid dynamic bearing 1 and the bearing portion 15 of the housing 5 electrically conductive, and therefore, static electricity occurring at the shaft 3 can be grounded via the housing 5.

[0021] The anionic antistatic additive (alkyl aryl sulfonate) has an affinity for the ester base oil (dioctyl

sebacate) and is contained at 1.0 percent by weight in the conductive oil. Therefore, the antistatic additive can produce sufficient conductivity for discharging the static electricity without impairing the lubrication performance of the oil. It is to be noted that the conductivity of oil becomes insufficient if the antistatic additive content is smaller than 0.1 percent by weight and becomes incapable of sufficiently discharging the static electricity. If the antistatic additive content exceeds 5 percent by weight, then the lubrication performance of oil is impaired. Therefore, by virtue of the fact that the anionic antistatic additive content is 1.0 percent by weight, the oil conduction performance and oil lubrication performance can be made compatible at the desired level.

[0022] The conductive oil of this embodiment contains 0.5 percent by weight of amine-based antioxidant, and therefore, the deterioration of oil due to oxidation can be restrained, and this enables the provision of a lubricant whose performance is stabilized for a long time. It is to be noted that a phenol-based antioxidant may be employed in place of the amine-based antioxidant. The content of this antioxidant should preferably be set within a range of 0.1 percent by weight to 5 percent by weight. An oxidation preventing ability becomes insufficient when the content is smaller than 0.1 percent by weight, and the original lubrication performance of oil is deteriorated when the content exceeds 5 percent by weight.

[0023] Although the dioctyl sebacate is employed as the ester base oil in the aforementioned embodiment, it is acceptable to employ pentaerythritol. Although the alkyl aryl sulfonate is employed as the anionic antistatic additive representative of the antistatic additive in the aforementioned embodiment, it is acceptable to employ alkyl benzene sulfonate or alkyl phosphate. It is also acceptable to employ a cationic antistatic additive of quaternary ammonium salt, amine salt or the like or an amphoteric antistatic additive of a betaine type or an alanine type. It is further acceptable to employ a nonionic antistatic additive of polyoxyethylene alkylamine or the like.

[0024] As is apparent from the above, the conductive lubricant for a fluid dynamic bearing of the present invention employs an ester base oil that concurrently has heat resistance, a small quantity of evaporation, low cost and wettability to metal, which are necessary for a fluid dynamic bearing. On this basis, an antistatic additive having an affinity for this ester base oil is contained at 0.1 to 5 percent by weight in the conductive lubricant. Therefore, according to the present invention, the conductive lubricant having conductivity by virtue of the antistatic additive contained therein makes the rotary side and the fixed side of the fluid dynamic bearing electrically conductive, thereby allowing the static electricity occurring at the fluid dynamic bearing to be grounded. The antistatic additive has an affinity for the ester base oil, and therefore, the lubrication performance is not impaired.

[0025] According to the conductive lubricant for the fluid dynamic bearing of one embodiment, the antistatic additive is contained at 0.5 to 2 percent by weight therein, and therefore, the conduction performance and lubrication performance of oil can be made compatible at the more desired level. 5

[0026] According to one embodiment, the antistatic additive can be provided by an anionic, cationic, amphoteric or nonionic antistatic additive.

[0027] The invention being thus described, it will be obvious that the same may be varied in many ways. Such variations are not to be regarded as a departure from the spirit and scope of the invention, and all such modifications as would be obvious to one skilled in the art are intended to be included within the scope of the following claims. 10 15

Claims

1. A conductive lubricant for a fluid dynamic bearing comprising: 20

an ester base oil and an antistatic additive having an affinity for the ester base oil, and the antistatic additive being contained at 0.1 to 5 percent by weight in the conductive lubricant. 25

2. A conductive lubricant for a fluid dynamic bearing as claimed in claim 1, wherein 30

the antistatic additive is contained at 0.5 to 2 percent by weight in the conductive lubricant.

3. A conductive lubricant for a fluid dynamic bearing as claimed in claim 1, wherein 35

the antistatic additive is an anionic, cationic, amphoteric or nonionic antistatic additive. 40


40

45

50

55

Fig.1





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 12 2834

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	WO 97 18562 A (PARSONEAULT NORBERT S ;KHAN RAQUIB U (US); LEUTHOLD HANS L (US); M) 22 May 1997 (1997-05-22) * page 8, line 22 - page 9, line 31 *	1-3	C10M169/04 G11B19/20 //(C10M169/04, 105:36,105:38, 133:06,133:08, 135:10, 137:02), C10N30:14, C10N40:18
X	US 4 604 229 A (RAJ KULDIP ET AL) 5 August 1986 (1986-08-05) * column 1, line 44 - line 51 * * column 3, line 9 - line 20 * * column 3, line 53 - line 61 * * column 4, line 29 - line 35 *	1-3	
X	EP 0 206 516 A (FERROFLUIDICS CORP) 30 December 1986 (1986-12-30) * page 6, line 1 - line 14 * * page 11, line 18 - page 12, line 11; example 2 *	1-3	
X	WO 97 16827 A (BORELIS LOUIS ;KHAN RAQUIB U (US); LEUTHOLD HANS (US); HEINE GUNTE) 9 May 1997 (1997-05-09) * page 4, line 6 - line 34 * * page 10, line 26 - line 32 * * page 11, line 7 - line 20 * * page 13, line 6 - line 13 *	1-3	
A	US 5 744 431 A (KARIS THOMAS EDWARD ET AL) 28 April 1998 (1998-04-28) * column 2, line 22 - line 31 * * column 2, line 34 - column 3, line 35 * * column 7, line 33 - line 46 *	1-3	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C10M G11B
Place of search THE HAGUE		Date of completion of the search 18 January 2001	Examiner Rotsaert, L
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/92 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 12 2834

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

18-01-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9718562 A	22-05-1997	CN 1200831 A	02-12-1998
		DE 19681651 T	15-10-1998
		GB 2322730 A,B	02-09-1998
		JP 2000500898 T	25-01-2000
		US 5940246 A	17-08-1999
US 4604229 A	05-08-1986	EP 0208391 A	14-01-1987
		JP 61275372 A	05-12-1986
		US 4732706 A	22-03-1988
		US 4673997 A	16-06-1987
		US 4687596 A	18-08-1987
EP 0206516 A	30-12-1986	US 4604222 A	05-08-1986
		US 4673997 A	16-06-1987
		JP 2590065 B	12-03-1997
		JP 61274737 A	04-12-1986
		US 4687596 A	18-08-1987
		JP 62109896 A	21-05-1987
WO 9716827 A	09-05-1997	CN 1200833 A	02-12-1998
		CN 1200834 A	02-12-1998
		DE 19681633 T	29-10-1998
		DE 19681634 T	03-12-1998
		GB 2344598 A,B	14-06-2000
		GB 2322728 A,B	02-09-1998
		GB 2322729 A,B	02-09-1998
		JP 11514778 T	14-12-1999
		JP 11514779 T	14-12-1999
		WO 9716828 A	09-05-1997
		WO 9716829 A	09-05-1997
		US 5930075 A	27-07-1999
US 5744431 A	28-04-1998	US 5907456 A	25-05-1999
		US 5641841 A	24-06-1997
		US 5886854 A	23-03-1999

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82